#### PIMA Technical Bulletin #104

# Fire Performance in Roof Systems

### **About Polyiso Insulation**

Polyiso is a rigid foam insulation used in more than 70% of commercial roof construction and offers a continuous insulation solution for commercial and residential wall assemblies. As one of North America's most widely used and readily available building products, Polyiso is a cost-effective insulation option for reducing building energy use and improving the overall service-life of roofs and walls.

The benefits of using Polyiso include:

- High R-value per inch of thickness
- Excellent fire test performance
- Extensive building code approvals
- Cost-effective continuous insulation (ci) solution
- Compatible with most roof and wall systems
- Dimensional stability
- Compressive strength
- Moisture resistance
- Thinner walls and roofs with shorter fasteners
- Long service life
- Preferred insurance ratings
- Virtually no global warming potential
- Zero ozone depletion potential
- Recyclable through reuse
- Recycled content (amount varies by product)
- Regional materials (nationwide production network)
- QualityMark<sup>CM</sup> certified LTTR-values



Continuous improvement in the product and years of rigorous testing mean POLYISO INSULATION OFFERS THE MOST EXTENSIVE RANGE OF CODE APPROVALS FOR INSULATION USE IN ROOF SYSTEMS. It remains the **only** foam plastic insulation product for direct application to steel deck to earn FM Approval for Class 1 Roof Systems. Polyiso is also classified by UL for use in roof systems with direct-to-steel-deck applications of foam plastic insulation under both single-ply and asphalt-based roof coverings.

### Polyiso Insulation is the Best Choice for Roof Systems

Polyiso is Used in All Types of Roof Systems

For new construction or re-roof projects, polyiso is the only foam plastic insulation that can be used in all types of roof systems:

- **Built-up Roofs:** Polyiso has high-temperature stability and will not melt, like thermoplastic insulation, when hot mopped with asphalt.
- **Modified Bitumen Roofs:** Polyiso performs successfully in modified bitumen systems, which are attached with high temperature methods or with hot asphalt.
- **Bitumen Roofs:** Polyiso performs successfully in modified bitumen systems, which are attached with high temperature methods or with hot asphalt.
- **Singly-ply Roofs:** Polyiso can be used in all three types of single-ply systems: loose-laid ballasted, fully adhered, and mechanically attached. Polyiso is unaffected by properly applied construction adhesives and can be used without the need for a cover board.
- **Metal Roofs:** Polyiso has excellent dimensional stability, which is important for these systems.

It is best to consult a specific polyiso manufacturer for its list of approvals for use in the desired system.

Polyiso is Easy to Specify

Polyiso insulation meets the requirements of ASTM C1289 Standard Specification for Faced Rigid Cellular Polyisocyanurate Insulation Board. Specifying insulation products for the roofing system with ASTM C1289, assures use of the best insulation product for the project.

## The Importance of Building Codes in Construction

Building codes are in place to provide a means to safeguard life and to protect the public welfare through regulating the design, construction practices, construction material quality (including fire performance), location, occupancy, and maintenance of buildings and structures. When regulating materials, many of the model building codes refer to quality standards developed by standard-setting organizations such as the American Society for Testing and Materials (ASTM). Some building codes and insurance rating organizations also rely on test information from FM Global (FM) and Underwriters Laboratories Inc. (UL).

## Foam Plastic Insulation and Building Codes

ICC model codes include specific sections pertaining to the safe use of foam plastics in construction. Generally, the codes require that the foam core have a flame spread rating of 75 or less and a smoke development rating of 450 or less, when tested in accordance with ASTM E84. Further, all foam plastics must be separated from the interior of a building by an approved thermal barrier such as 1/2 inch gypsum board. For roofing applications, the smoke development rating does not apply. The elimination of the thermal barrier is allowed only under very specific conditions.

Direct Application of Foam Plastic Insulation to Steel Decks

Polyiso is still the **only foam plastic insulation** product to have direct-to-steel-deck approvals from both FM and UL. FM approval for Class 1 roof systems was granted by passing FM 4450 and UL approval was earned by passing UL 1256. Both of these tests are specifically referenced in many building codes.

For example, in the International Building Code (IBC), the requirements for a thermal barrier are not applicable to foam plastic roof insulation used in roof deck construction that complies as an assembly with FM 4450 or UL 1256. For all roof applications, the smoke developed rating shall not be applicable.

Both the IBC and International Residential Code (IRC) have similar requirements. Polyiso insulation first successfully passed UL 1256 over 20 years ago and today satisfies the major share of the market's demand for "direct-to-steel-deck" applications.

Importance of FM 4450 Calorimeter Test and UL 1256 Resistance to Interior Fire Spread Test The spread of fire on the underside of a roof deck is a concern when buildings have large, open interior space, such as a warehouse or manufacturing facility. The two fire tests used by code bodies to evaluate the spread of fire in this manner are FM 4450 (also called the FM Calorimeter Test) and UL 1256 (also known as the Resistance to Interior Fire Spread Test). While both tests evaluate the entire roof assembly from deck to roof covering, the test conditions and test pass criteria are very different:

	FM 4450	UL 1256
Exposed Sample Size	4 feet x 4 feet	1.48 feet x 24 feet
Test Duration	30 min.	30 min.
Fuel Source/Rate (Btu/min.)	Heptane/Propane / 26,400	Natural Gas / 5,000
Temperature @ 10 min.	1500 degrees F	580°F (Vent and with non-combustible callibration sample)
Temperature @ 30 min.	1600 degrees F	NA
Pass Criteria	No external flaming; no dropping of flaming particles into the furnace	Flame spread @ 10min. less than 10 feet; 30 mins. flame spread less than 14 feet; subjective on thermal degradation and "combustive" damage
Pass Criteria, Maximum Fuel Contribution (Btu/ft2/min.)	3 min. 410 5 min. 390 10 min. 360 30 min. 285 (avg.)	NA

Not all foam plastic insulations perform equally in these tests. Polyiso is a thermoset material and withstands high temperatures which accounts for its successful performance in both FM 4450 Calorimeter and ANSI/UL 1256 testing. Other foam plastic insulations, like polystyrene, are thermoplastic materials which soften at 165° F and melt between 200° F and 210° F, long before the standard 30 minute fire exposure is ended. Because of the high temperatures reached in the FM 4450 Calorimeter test, the polystyrene melts through the seams of the steel deck, spreads fire on the underside of the deck during the test and liberates flaming particles into the furnace. Accordingly, the FM Approval Guide does not list any Class 1 Roof Systems approvals for the use of polystyrene insulation in a direct to steel deck application (i.e., without the use of a thermal barrier).

Only roof assemblies that pass FM 4450 may be used in FM insured buildings.

#### **PIMA**

For more than 30 years, PIMA (Polyisocyanurate Insulation Manufacturers Association) has served as the unified voice of the rigid polyiso industry proactively advocating for safe, cost-effective, sustainable and energy-efficient construction. PIMA's membership includes manufacturers of polyiso insulation and suppliers to the industry. The products of PIMA's members comprise the majority of the polyiso produced in North America.

PIMA produces technical bulletins to address frequently asked questions about polyiso insulation. These publications update and inform architects, specifiers, and contractors about and build consensus on the performance characteristics of polyiso insulation. Individual companies can provide specific information about their respective polyiso products.

For more information on polyisocyanurate insulation, visit www.polyiso.org



www.polyiso.org • pima@pima.org 1220 North Fillmore Street, Suite 400

Arlington, VA 22201 Phone: 703.258.0093













