

DESCRIPTION

Closed-cell polyisocyanurate (polyiso) foam core integrally bonded to inorganic coated glass facers (CGF) on both sides. Available in 0.5" thick 4ft x 8ft (1220mm x 2440mm) and 0.5" Thick 4ft x 4ft (1220mm x 1220mm) panels. Manufactured in accordance with **ASTM C1289, Type II, Class 4, Grade 1 (80 psi (551 kPa) minimum, up to 110 psi (758 kPa) compressive strength) and CAN/ULC-S704 Type 4, Class 3.**

APPLICATIONS

Manufactured and tested for use in new and re-roofing applications. ACFoam[®]-HD CoverBoard is used in mechanically attached single-ply, fully adhered single-ply, and self-adhered "peel & stick" roofing systems. These roofing systems depend on proper installation for successful performance. Refer to roof cover manufacturer, FM Approvals[®] RoofNav and UL Product iQ[®] for additional application details.

INSTALLATION

ACFoam-HD CoverBoard shall be kept dry before, during and after installation. This product will burn if exposed to an ignition source of sufficient heat and intensity. Do not apply flame directly to ACFoam-HD CoverBoard insulation. Refer to product packaging, Atlas Technical Bulletin #12 and *PIMA Technical Bulletin #109* for storage and handling recommendations. To minimize the effect of thermal bridging, and the impact of moisture/airflow into the roof system, Atlas strongly recommends the ACFoam be installed in multiple layers. Please reference the ACFoam Fastening Pattern Guide for General Installation, Usage Instructions, and Warranty information for ACFoam products. Typical field fastening requirements can be obtained from roof cover manufacturer and/or FM Approvals RoofNav and FM Global Loss Prevention Data Sheet 1-29. Prior to installation, Atlas Roofing Corporation recommends, as applicable, you consult with your local building code official(s), contract documents, design professional, and all other relevant parties to ensure appropriate compliance.

PHYSICAL PROPERTIES

ACFOAM-HD COVERBOARD MEETS OR EXCEEDS THE FOLLOWING PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	ASTM C1289 OR CAN/ULC S704 (MIN REQUIREMENTS)
DIMENSIONAL STABILITY	ASTM D2126	<0.5%
COMPRESSIVE STRENGTH	ASTM D1621	¹ Grade 1
WATER ABSORPTION	ASTM C209	<4.0%
	ASTM C1763	<4.0%
	ASTM D2842	<3.5%
WATER VAPOR TRANSMISSION	ASTM E96	<1.5 perm (85.8ng/(Pa*s*m ²))
FLAME SPREAD	ASTM E84/UL723	² <75
SMOKE DEVELOPMENT	ASTM E84/UL723	² <450
TENSILE STRENGTH	ASTM D1623	>2000 psf (95 kPa)
SERVICE TEMPERATURE	-	-100° to +250°F

¹80 psi (551 kPa) minimum, up to 110 psi (758 kPa)

²Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of ≤ 75 and smoke development ≤ 450 meet code requirements for foam plastic roof insulation. Physical properties listed above are presented as typical average values as determined by referenced ASTM test methods and are subject to normal manufacturing variation.

CODE COMPLIANCE

- **ASTM C1289, Type II, Class 4, Grade 1**
- **CAN/ULC-S704, Type 4, Class 3**
- **UL Certified for Canada** – Insulated Roof Deck Assemblies Construction No. C38 and 52. Meet CAN/ULC-S126, CAN/ULC-S101 and CAN/ULC-S107
- **UL 1256 Classification** Construction No. 120, 123 & 292
- **UL 790 (ASTM E108)** Roofing Systems Classification
- **UL 263 (ASTM E119)** Fire Resistance Classification
- **FM 4450/4470** Refer to FM Approvals[®] RoofNav for Specific System Details
- **FM 4473 rated SH-1** for Severe Hail
- **UL Class B** Over Combustible Decks with UL Classified Membranes
- **IBC Chapter 26 & NBC** Sections on Foam Insulation
- **Miami-Dade**, NOA No. 17-1211.05
- **Florida Product Approval**, No. FL17989
- **GREENGUARD GOLD Certified**
- **UL 2824** Resistant to Mold Growth as Validated by UL Environment

PRODUCT DATA

THICKNESS	THERMAL RESISTANCE		PIECES PER UNIT	SQUARE FT PER UNIT		TRUCKLOAD QUANTITIES (SQUARES)	AVERAGE WEIGHT (LB/SF)	RECYCLED CONTENT		
	¹ R-VALUE	² RSI		4×8	4×4			POST CONSUMER	PRE CONSUMER	TOTAL
0.50"	2.5	0.44	42	1,344	672	645.12	0.50	-	7.4%	7.4%

¹Conditioned thermal values were determined by ASTM Test Method C 518 at 75° mean temperature. Test specimens were conditioned in accordance with procedures outlined in ASTM C1289, Section 11.1.2.1. Test samples were third-party selected and tested by an accredited material testing laboratory.

²RSI is the metric expression of R-value (m² • K/W).

To minimize the effects of thermal bridging, and the impact of moisture/airflow into the roof system, Atlas strongly recommends the ACFoam insulation assembly be installed in multiple layers.

WARRANTY

ACFoam-HD CoverBoard is backed by a Limited 20-Year Thermal Warranty. For complete terms and conditions, visit roof.atlasrwi.com/warranty

FOR A COMPLETE LIST OF PRODUCT SIZES, SCAN OR CLICK QR CODE TO DOWNLOAD THE PACKAGE & LOADING GUIDE



SUSTAINABILITY

Atlas polyiso insulation is manufactured using environmentally responsible processes and formulations.

- Contains no CFCs, HCFCs or HFCs
- Zero Ozone Depletion Potential (ODP)
- Negligible Global Warming Potential (GWP)
- GREENGUARD Gold Certification
- Contributes to LEED credits

For more information visit roof.atlasrwi.com/about-roof/sustainability

FASTENING GUIDELINES

THICKNESS	FM RATING	FIELD FASTENERS PER 4×8' BOARD
0.5"	1-75	12
	1-90	16

Other than the aforementioned representations and descriptions, Atlas Roofing Corporation (hereafter, "Seller") makes no other representations or warranties as to the insulation sold herein. The Seller disclaims all other warranties, express or implied, including the warranty of merchantability and the warranty of fitness for a particular purpose. Seller does, however, have a limited warranty as to the LTTR-Value of the insulation, the terms of which are available upon request from the Seller. Seller shall not be liable for any incidental or consequential damages including but not limited to the cost of installation, removal, repair or replacement of this product. Buyer's remedies shall be limited exclusively to, at Seller's option, the repayment of the purchase price or resupply of product manufactured by Atlas in a quantity equal to that of the nonconforming product. Atlas distributors, agents, salespersons or other independent representatives have no authority to waive or alter the above limitation of liability and remedies.



Atlas Roofing Corporation
 2000 Riveredge Parkway, Suite 800 • Atlanta, GA • 30328
 770-952-1442 • roof.atlasrwi.com

